

Rev: September 2015

CHEMICAL RESISTANCE

ASTM F925 Resistance to Chemicals

	Surface Dulling		Surface Attack		Color Change	
	1 Hour	24 Hours	1 Hour	24 Hours	1 Hour	24 Hours
Acids						
Acetic Acid- 28%	0	0	0	0	0	0
Citric Acid - 10%	0	0	0	0	0	0
Hydrochloric Acid- 10%	0	0	0	0	0	0
Sulfuric Acid- 10%	0	0	0	0	0	0
Bases / Alkalis						
Ammonia 5%	0	0	0	0	0	0
Ammonium Hydroxide - 10%	0	0	0	0	0	0
Ammonium Hydroxide - 30%	0	0	0	0	0	0
Sodium Carbonate - 10%	0	0	0	0	0	0
Sodium Hydroxide - 10%	0	0	0	0	0	0
Alcohols						
Ethyl (Denatured) Alcohol - 30%	0	0	0	0	0	0
Ethyl (Denatured) Alcohol - 70%	0	0	0	0	0	0
Ethyl (Denatured) Alcohol - 90%	0	0	0	0	0	0
Hand Sanitizer (Alcohol Based)	0	0	0	0	0	0
Rubbing Alcohol (70% Isopropyl)	0	0	0	0	0	0
Aromatics						
Crude Oil	0	0	0	0	0	0
Fuel Oil #1	0	0	0	0	0	0
Kerosene	0	0	0	0	0	0
Mineral Spirits (White Spirit)	0	0	0	0	0	0
Turpentine	0	0	0	0	0	0
Unleaded Gasoline (Regular Grade)	0	0	0	0	0	0
Phenol	0	0	0	0	0	0
Disinfectants / Cleaners						
Bleach 5%	0	0	0	0	0	0
Formaldehyde - 37%	0	0	0	0	0	0
Quaternary Ammonium Disinfectant Cleaner	0	0	0	0	0	0



<u>Hospital Chemicals</u>	<u>Surface Dulling</u>		<u>Surface Attack</u>		<u>Color Change</u>	
	<u>1 Hour</u>	<u>24 Hours</u>	<u>1 Hour</u>	<u>24 Hours</u>	<u>1 Hour</u>	<u>24 Hours</u>
Aniline Blue - 2.5	0	0	0	0	0	0
Betadine Skin Cleanser	0	0	0	0	0	0
Betadine Solution - 10%	0	0	0	0	0	0
Iodine Tincture	0	0	0	0	0	0
Iodine Gram Stain	0	0	0	0	0	0
Mineral Oil (medicinal grade)	0	0	0	0	0	0
Potassium Permanganate- 1.5%	0	0	0	0	0	0
Silver Nitrate - 5%	0	0	0	0	0	0
Tincture of Benzoin	0	0	0	0	0	0
Urea Solution	0	0	0	0	0	0
Wright's Blood Stain	0	0	0	0	0	0

Ratings Key:

- 0 - No Change
- 1 - Slight Change
- 2 - Moderate Change
- 3 - Severe Change